

ENTEX™ 53061

SOFT POLYURETHANE ENCAPSULANT

TECHNICAL DATA **MARCH 2016**

Product Description

Soft, flexible, water white clear, non-yellowing, LED Encapsulation. Low temperature stable.

APPLICATIONS

- LED Encapsulation
- Lighting Arrays

FEATURES

- RoHS & REACH Compliant
- Clear
- Non-Yellowing
- Soft and Flexible

SUBSTRATES

- Plastics
- Metals
- Glass

PACKAGING

- Dual Cartridges
- Bulk

TYPICAL PROPERTIES OF UNCURED MATERIAL		
Property	Value, Part A	Value, Part B
Chemical Class	Isocyanate	Polyol
Appearance	Clear	Clear
Viscosity, 10 RPM @ 25°C, cps	10,500 to 14,500	400 to 550
Viscosity, 100 RPM @ 25°C, cps	11,000 to 14,500	400 to 500
Specific Gravity	1.12	1.11
Mix Ratio by Volume	1	1

TYPICAL PROPERTIES OF CURED MATERIAL	
Property	Value
Glass Transition Temperature (Tg), °C	-40
Lap Shear Strength, Al/Al, PSI	-
Hardness, Shore	A77
Ultimate Tensile Strength, PSI	-
Elongation at Break, %	-
Operating Temperature (°C)	-50 to 120
Volume Resistivity, Ω-cm	-

***All properties given are typical values and are not intended for use in preparing specifications.**

PROCESSING	
Gel Time (15cc mass), Min	10
Cure Options: Hrs @ 25°C	24
Clean-Up Solvent	Isopropyl Alcohol

SHELF LIFE, STORAGE

18 ± 10°C 1 Year DOM

MATERIAL IS MOISTURE SENSITIVE. CONSULT SDS FOR SAFE HANDLING RECOMMENDATIONS.

THIS MATERIAL IS SOLD FOR INDUSTRIAL USE ONLY

RESIN DESIGNS, LLC MAKES NO EXPRESS OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. RESIN DESIGNS' LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT.