

NEXUS™ 52101

POLYURETHANE ADHESIVE AND ENCAPSULANT

TECHNICAL DATA
February 2016
Product Description

General purpose adhesive, encapsulant, plastic bonder. High Performance clear and flexible polycarbonate bonder.

APPLICATIONS

- Automotive
- Bonding Plastics
- Encapsulant
- Potting

FEATURES

- RoHS & REACH Compliant
- Clear
- Flexible
- Low Temp Performance

SUBSTRATES

- Polycarbonate
- Metals
- Glass
- Hard to Bond Plastic

PACKAGING

- Dual Cartridges

TYPICAL PROPERTIES OF UNCURED MATERIAL

Property	Value, Part A	Value, Part B
Chemical Class	Isocyanate	Polyol
Appearance	Clear	Clear
Viscosity, 10 RPM @ 25°C, cps	7,000 to 11,000	1,000 to 2,000
Viscosity, 100 RPM @ 25°C, cps	7,000 to 11,000	1,000 to 2,000
Specific Gravity	1.11	1.05
Mix Ratio by Volume	1	1

TYPICAL PROPERTIES OF CURED MATERIAL

Property	Value
Glass Transition Temperature (T _g), °C	-20
Lap Shear Strength, Al/Al, PSI	> 1850
Hardness, Shore	D45
Ultimate Tensile Strength, PSI	> 500
Elongation at Break, %	170
Volume Resistivity, Ω-cm	1 x 10 ¹⁵

***All properties given are typical values and are not intended for use in preparing specifications.**

CURE OVERVIEW

Gel Time (15cc mass), Min	8 to 10
Cure Options: Hrs @ 25°C; Min @ 65°C	24; 30 to 45
Clean-Up Solvent	Isopropyl Alcohol

SHELF LIFE, STORAGE

18 ± 10°C 1 Year DOM

MATERIAL IS MOISTURE SENSITIVE. CONSULT SDS FOR SAFE HANDLING RECOMMENDATIONS.

THIS MATERIAL IS SOLD FOR INDUSTRIAL USE ONLY

RESIN DESIGNS, LLC MAKES NO EXPRESS OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. RESIN DESIGNS' LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT.