

VIVID CURE™ 70201

UV CURE FIP GASKET MATERIAL

TECHNICAL DATA

MARCH 2016

Product Description

Soft, one part, UV cure, form-in-place gasket material with excellent moisture resistance and vibration dampening that provides selective release from bonded or coated substrates. Low viscosity.

APPLICATIONS

- Gasket
- Vibration
- Dampening

FEATURES

- RoHS & REACH Compliant
- Moisture Resistant
- Low Viscosity

SUBSTRATES

- Plastics
- Metals
- Glass

PACKAGING

- Syringes
- Bulk

TYPICAL PROPERTIES OF UNCURED MATERIAL

Property	Value
Chemical Class	UV Acrylate
Appearance	Clear
Viscosity @ 25°C, cps	13,000 to 24,000
Specific Gravity	1.13

TYPICAL PROPERTIES OF CURED MATERIAL

Property	Value
Glass Transition Temperature (T _g), °C	-50
Hardness, Shore	A45
Operating Temperature Range, °C	-50 to 130
Elongation at Break, %	300

***All properties given are typical values and are not intended for use in preparing specifications.**

CURE OVERVIEW

Cure Options	UV cure @ 200 mW/cm ² minimum. 365, 405 nm recommended.
Clean-Up Solvent	Isopropyl Alcohol

SHELF LIFE, STORAGE

18 ± 10°C 1 Year DOM

MATERIAL IS LIGHT SENSITIVE. CONSULT SDS FOR SAFE HANDLING RECOMMENDATIONS.

THIS MATERIAL IS SOLD FOR INDUSTRIAL USE ONLY

RESIN DESIGNS MAKES NO EXPRESS OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. RESIN DESIGNS' LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT.