

VIVID CURE™ 86011

UV CURE EPOXY

TECHNICAL DATA **APRIL 2016**

Product Description

An epoxy-based, cationic-curable adhesive and/or sealant. This product is activated by exposure to medium intensity UV radiation resulting in a high strength, chemical resistant, low outgassing polymer system capable of surviving exposure up to 200°C.

APPLICATIONS

- Electronics
- Encapsulation
- Sealant

FEATURES

- RoHS & REACH Compliant
- Excellent Chemical Resistance
- High Hardness
- Fast UV Cure

SUBSTRATES

- Metals
- Ceramics
- Glass

PACKAGING

- Syringes
- Bulk

TYPICAL PROPERTIES OF UNCURED MATERIAL	
Property	Value
Chemical Class	UV Epoxy
Appearance	Clear
Viscosity, 10 RPM @ 25°C, cps	2,000 to 3,500
Viscosity, 100 RPM @ 25°C, cps	2,000 to 3,000
Specific Gravity	1.16

TYPICAL PROPERTIES OF CURED MATERIAL	
Property	Value
Glass Transition Temperature (Tg), °C	135
Hardness, Shore	D80
Ultimate Tensile Strength, PSI	5,000
Elongation at Break, %	4
Operating Temperature Range, °C	-10 to 200
Volume Resistivity, Ω-cm	1 x 10 ¹⁵

***All properties given are typical values and are not intended for use in preparing specifications.**

CURE OVERVIEW	
Cure Options	UV Cure, optimum wavelength is 310 nm.
Clean-Up Solvent	Isopropyl Alcohol

SHELF LIFE, STORAGE

18 ± 10°C 1 Year DOM

MATERIAL IS LIGHT SENSITIVE. CONSULT SDS FOR SAFE HANDLING RECOMMENDATIONS.

THIS MATERIAL IS SOLD FOR INDUSTRIAL USE ONLY

RESIN DESIGNS MAKES NO EXPRESS OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. RESIN DESIGNS' LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT.